

## Product Data Sheet

# Bar Solder

### Introduction

Indium Corporation manufactures **bar solder** specifically to surpass the strict quality demands of the surface mount industry in order to provide more consistent and reliable performance. **Bar solder** is available in a full range of SnPb and Pb-free alloys, including industry standard Sn63, and SAC305. To eliminate the chance of contaminating Pb-free solder with Pb, ingots come in two shapes to designate the alloy. All **bar solder** complies with the requirements of ASTM B-32, J-Std 006 (formerly QQS-571F) and JIS Z 3282.

Indium Corporation also features RoHS compliant **Sn995 Pb-Free Bar Solder** (99.5Sn, 0.5Cu + Co), which is manufactured from electrolytically processed tin, copper and cobalt to create a solder so pure it far exceeds the most common specification requirements. The addition of cobalt forms shiny, uniform joints, and reduces the amount of dross generated during wave soldering. The melting point is approximately 228°C and recommended operating temperatures are between 260-270°C.



Pb-Free Bar Solder

### Standard Packaging and Availability

**Bar solder** ingots are packed in 25lb. boxes. Deliveries can be arranged to suit your production schedule.



SnPb Bar Solder

### Technical Support

Indium Corporation's internationally experienced engineers provide in-depth technical assistance to our customers. Thoroughly knowledgeable in all facets of material science as it applies to the electronics and semiconductor sectors, Technical Support Engineers provide expert advice in solder properties, alloy compatibility and selection of solder preforms, wire, ribbon and paste. Indium Corporation's Technical Support Engineers provide rapid response to all technical inquiries.

### Material Safety Data Sheet

The MSDS for this product can be found online at <http://www.indium.com/techlibrary/msds.php>

### Ask Us About...

The Solder and Solder Dross Recycle Program is a service offered by Indium Corporation to complete the usage cycle for bar solder. Up to 50% of bar solder used in wave soldering will be converted to dross, which still contains mostly usable metal. Indium Corporation can recycle these materials and return the metal value to you as a credit, or convert them to usable bar for a fee. During an alloy switch-over, use Indium Corporation's recycling service to reclaim value on the pot dump and leftover bar. For more information about our Solder and Solder Dross Recycle Program, please send an email to [askus@indium.com](mailto:askus@indium.com).

This product data sheet is provided for general information only. It is not intended, described which are sold subject exclusively to written warranties and limitations and shall not be construed, to warrant or guarantee the performance of the products thereon included in product packaging and invoices.

Form No. 98425 R4

[www.indium.com](http://www.indium.com)

[askus@indium.com](mailto:askus@indium.com)

ASIA: Singapore, Cheongju: +65 6268 8678  
 CHINA: Suzhou, Shenzhen, Liuzhou: +86 (0)512 628 34900  
 EUROPE: Milton Keynes, Torino: +44 (0) 1908 580400  
 USA: Utica, Clinton, Chicago: +1 315 853 4900



ISO 9001  
REGISTERED