



## SAFETY DATA SHEET

This safety data sheet covers metal mixtures using tin with no lead. See alloy table for all possible combinations.

### 1. PRODUCT AND COMPANY IDENTIFICATION

**Product Identifier:** TIN BASED ALLOYS (NO LEAD)

**SDS Number:** SDS-972

**Revised Date:** 14 DECEMBER 2017

**Product Use:** Industrial Use - Alloy Metal Mix with Tin as the base. (See alloy table for product listing of metal Mixes and combinations).

#### MANUFACTURER:

##### In America:

The Indium Corporation of America  
34 Robinson Rd., Clinton, New York 13323  
Information: (315) 853-4900  
nswarts@indium.com

Indium Corporation of America  
Chicago Materials Division  
80 Scott Street  
Elk Grove Village, Illinois 60007  
Information: (847) 439-9135

##### In Europe:

Indium Corporation of Europe  
7 Newmarket Ct.  
Kingston, Milton Keynes, UK, MK 10 OAG  
Information: +44 [0] 1908 580400

##### In Asia:

The Indium Corporation of America  
Asia-Pacific Operations-Singapore  
29 Kian Teck Avenue  
Singapore 628908  
Information: +65 6268-8678

##### EMERGENCY PHONE:

**CHEMTREC 24 hrs.**

**USA: 1 (800) 424-9300**

**Outside USA: +1 (703) 527-3887**

##### In China:

Indium Corporation (Suzhou), Co., Ltd.  
No. 428 Xinglong Street  
Suzhou Industrial Park  
Suchun Industrial Square  
Unit No. 14-C  
Jiangsu Province, China 215126  
Information: (86) 512-6283-4900

web page : <http://www.indium.com>

## 2. HAZARDS IDENTIFICATION

### PRIMARY ROUTES OF ENTRY:

⊕Eye    ⊕Inhalation    ⊕Skin    ⊕Ingestion    NTP\*    IARC    OSHA    ⊕Not Listed

### Carcinogen listed in

GHS:

Note: Some tin metal mixtures may not require a pictogram or include any hazard statements. Review product labeling.



Signal Word: Warning

#### Hazard statement(s)

H335                    May cause respiratory irritation (other metals not tin)

#### Precautionary statement(s)

P233                    Keep container tightly closed  
 P261                    Avoid breathing dust/fume/gas/mist/vapors/spray  
 P270                    Do not eat, drink or smoke when using this product  
 P273                    Avoid release to the environment  
 P280                    Wear protective gloves/protective clothing/eye protection/face protection  
 P362 +P364            Take off contaminated clothing and wash before reuse  
 P301 + P314            IF SWALLOWED: Get Medical advice/attention if you feel unwell  
 P302 +P352            IF ON SKIN: Wash with plenty of soap and water  
 P304 + 341            IF INHALED: If breathing is difficult, remove victim to fresh air and keep at rest in a position comfortable for breathing  
 P305 + 351            IF IN EYES: Rinse continuously with water for several minutes (15 mins)  
 P501                    Dispose of in accordance with applicable local/state and federal regulations. Consider recycling.

### POTENTIAL HEALTH EFFECTS:

**Eye Contact:**        Solid metal does not pose a hazard. Contact with powdered metal alloy or fume from molten metal may cause irritation. Severe eye damage may result from hot molten metal being splashed into the eyes. Dust may cause irritation.

**Ingestion:**            Not generally considered toxic, but large amounts may cause irritation.

**Inhalation:**          Dust may cause irritation to the respiratory tract. Inhalation of zinc dust may cause a sweet taste, throat dryness, cough nausea and fever.

**Skin Contact:**        Mechanical irritant upon contact. Cannot be absorbed through skin. Hot molten metal may cause burns to the skin. **Antimony, Zinc, Cobalt and Nickel** – have been known to cause dermatitis.

**Chronic:**              Standard metal does not pose a hazard. However, melting, cutting, burning, or grinding may cause hazards: irritation or harm. Prolonged inhalation may cause harm.

**Silver** – chronic skin contact or ingestion of silver dusts, salts or fume can result in a condition known as Argyria, a condition with bluish pigmentation of the skin and eyes.

**Indium** – may cause damage to respiratory system if inhaled over long periods of exposure.

**Copper** – over exposure to fumes may cause metal fume fever (chills, muscle aches, fever, dry throat, cough, weakness, lassitude), metallic or sweet taste, discoloration of skin and hair.

**Nickel** – poison by ingestion. Can cause pulmonary asthma, and hypersensitivity.

**Tin** – prolonged inhalation of dust or fume may result in irritation of the lungs.

**Aluminum** – inhalation of finely divided powder has been reported to cause pulmonary fibrosis.

**Note:** The Indium Corporation does not recommend, manufacture, market or endorse any of its products for human consumption.

**Warning:** This product may contain a chemical (s) known to the State of California to cause cancer and birth defects (or other reproductive harm). (nickel and trace levels of lead not intentionally added) Applicable in the State of California .

### 3. COMPOSITION / INFORMATION ON INGREDIENTS

Components	% wt	CAS Registry #/EINECS #	PEL mg/m <sup>3</sup>	TLV-TWA mg/m <sup>3</sup>	TLV-STEL mg/m <sup>3</sup>
TIN	*	7440-31-5/231-141-8			
		(US)	2	2	-
		(EU)	-	2	4
		(Canada)	-	2	4
		(Singapore)	2	-	-
SILVER	*	7440-22-4/231-131-3			
		(US)	0.01	0.1	-
		(EU)	-	0.1	-
		(Canada)	-	0.1	0.3
		(Mexico)	-	0.1	-
		(Singapore)	0.1	-	-
INDIUM	*	7440-74-6/231-180-0			
		(US)	0.1	0.1	-
		(EU)	-	0.1	0.3
		(Canada)	-	0.1	0.3

		(Mexico)	-	0.1	0.3	
		(Singapore)	0.1	-	-	
		(China)	-	0.1	0.3	
COPPER	*	7440-50-8/231-159-6				
		(US)	0.1	0.2	-	
		(EU)	-	0.2(fume)	2(dust)	
		(Canada)	-	0.2	0.6	
		(Mexico)	-	0.2	2	
		(Singapore)	0.2 (fume)	1 (dust)	-	
		(China)	-	1(dust)	2.5(dust)	
			-	0.2(fume)	0.6(fume)	
ANTIMONY	*	7440-36-0/231-146-5				
		(US)	0.5	0.5	-	
		(EU)	0.5	-	-	
		(Canada)	-	0.5	1.5	
		(Mexico)	-	0.5	-	
		(Singapore)	0.5	-	-	
		(China)	-	0.5	-	
ZINC	*	7440-66-6/231-175-3		N.E.	N.E.	N.E.
NICKEL	*	7440-02-0/231-111-4				
		(US)	1	1.5	-	
		(Canada)	-	1	2	
		(Mexico)	-	1	-	
		(Singapore)	1	-	-	
		(China)	-	1	2.5	
ALUMINUM	*	7429-90-5	10	10	-	
		(EU)	-	10	-	
		(Canada)	-	10	20	
		(Mexico)	5	-	-	
		(Singapore)	10	-	-	
		(China)	-	3	-	
COBALT	*	7440-48-4	0.1	0.02	-	
		(EU)	-	0.1	-	

		(Canada)	-	0.05	0.1
		(Singapore)	0.02	-	-
TITANIUM	(TRACE)	7440-32-6	N.E.	N.E.	N.E.
MANGANESE	(TRACE)	7439-96-5	1(NIOSH)	0.2	3
		(EU)	-	1(fume)	3(fume)
		(Canada)	-	1(fume)	3(fume)
		(Singapore)	5(dust)	1(fume)	3(fume)
		(Mexico)	-	1(fume)	3(fume)
CERIUM	(TRACE)	7440-45-1	N.E.	N.E.	N.E.
BISMUTH	*	7440-69-9/231-177-4	N.E.	N.E.	N.E.
GERMANIUM	*	7440-56-4	N.E.	N.E.	N.E.

\* SEE ALLOY TABLE FOR PRODUCT MIX PAGE 9

N.E. = Not Established

#### 4. FIRST AID MEASURES

**Eye Contact:** Hold eyelids apart and flush eyes with plenty of tepid water for at least 15 minutes. Seek medical attention if irritation persists.

**Ingestion:** If patient is conscious, ONLY induce vomiting as directed by trained personnel. NEVER give anything by mouth to an unconscious person. Seek medical attention immediately.

**Inhalation:** Remove to fresh air. If not breathing, give artificial respiration or oxygen by trained personnel. Seek immediate medical attention.

**Skin Contact:** Remove contaminated clothing. Wash affected area with soap and water. Wash clothing before reuse. If irritation persists, obtain medical attention.

#### 5. FIRE FIGHTING MEASURES

**Flash Point:** Not established. **Method:** Not established.

**Auto-ignition Temperature:** Not applicable

**Flammable Limits:** Fine dusts and powders could be a potential explosion hazard.

**Extinguishing Media:** Use extinguishers appropriate for the surrounding fire conditions. Use dry sand, sodium chloride, or dolomite. Water, A/B/C extinguishers and halogenated agents are not recommended.

**Special Fire Fighting Procedures:** Firefighters wear an approved self-contained breathing apparatus and full protective clothing.

## 6. ACCIDENTAL RELEASE MEASURES

**Spill or Leak Procedures:** Wear respirator and other personal protective clothing. (See Exposure Controls/Personal Protection Section). Extinguish or remove all sources of ignition. Ventilate area. Clean up spill without generating or dispersing dust into the air. Vacuum solids instead of sweeping using a grounded unit. Reduce airborne dust and prevent scattering by moistening with water. Place spilt material in a container and dispose of in accordance with applicable regulations.

## 7. HANDLING AND STORAGE

**Handling Precautions:** Avoid breathing vapors from heated material and dusts from cutting or grinding. Avoid contact with eyes, skin and clothing. Follow routine safe handling procedures. Use with adequate ventilation.

**Storage Precautions:** Keep away from heat and flame. Store in suitable, tightly capped, and labeled containers in cool dry, well-ventilated area. Empty containers may be hazardous as they contain product residue.

## 8. EXPOSURE CONTROLS / PERSONAL PROTECTION

**Engineering Controls:** Local exhaust ventilation or point source exhaust ventilation is recommended to control any air contaminants or potential exposure. Keep exposures below regulatory limits.

### Personal protection:

**Eyes:** Chemical safety glasses/goggles. Face shield recommended when handling molten metal.

**Respirator:** An authority approved or compliant marked air-purifying respirator with a fume/dust chemical cartridge is recommended under certain circumstances where airborne concentrations are expected to be elevated. Warning: Air purifying respirators do not protect the worker in oxygen-deficient atmospheres.

**Skin:** Wear protective gloves. Hot gloves for handling molten metal.

**Other:** Eye-wash fountain/shower in work area. Avoid the use of contact lenses in high fume and dust areas.

**Work/Hygienic** Maintain good housekeeping. Clean up spills immediately. Good personal hygiene is essential. Avoid eating, smoking or drinking in the work area. Wash hands thoroughly with soap and water immediately upon leaving the work area.

## 9. PHYSICAL AND CHEMICAL PROPERTIES

<b>Appearance:</b>	Solid	<b>Boiling Point:</b>	Not available
<b>Odor:</b>	Odorless	<b>Melting Point:</b>	See Table
<b>Specific Gravity:</b>	See Table	<b>pH:</b>	Not applicable
<b>Vapor Pressure:</b>	Not available	<b>Solubility in Water:</b>	Insoluble
<b>Vapor Density:</b>	(air=1) Not applicable.		

## 10. STABILITY AND REACTIVITY

**General:** Stable.

**Conditions to Avoid:** Heat, flame, ignition sources

<b>Incompatible Materials:</b>	Halogens, sulfur and some acids
<b>Hazardous Decomposition / Combustion:</b>	None
<b>Hazardous Polymerization:</b>	Will not occur.

## 11. TOXICOLOGICAL INFORMATION

<b>Carcinogenicity:</b>	<b>NTP (National Toxicity Program):</b>	Yes - Nickel	
	<b>OSHA (Occupational Safety &amp; Health Administration):</b>	No	
	<b>IARC (International Agency for Research on Cancer):</b>	Yes - Nickel	
<b>LD50:</b>	Not established.	<b>LC50:</b>	Not established.
<b>Other:</b>	NICKEL RTECS# QR5950000 TIN RTECS# XP7320000, SILVER RTECS# VW3500000 ANTIMONY RTECS# CC4025000, INDIUM RTECS# NL1050000, COPPER RTECS# GL7900000		
	RTECS = NIOSH Registry of Toxic Effects of Chemical Substances		
	Product mixture not tested.		

## 12. ECOLOGICAL INFORMATION

Product not tested.

## 13. DISPOSAL CONSIDERATION

**Waste Disposal Method:** Scrap metal alloy usually has value. Contact a commercial reclaimer for recycling. Otherwise, dispose of in accordance with all Federal, State and Local environmental regulations. In Europe follow the Special Waste Regulations.

## 14. TRANSPORT INFORMATION

Transport in accordance with applicable regulations and requirements. Not regulated under US DOT (United States Department of Transportation). Non - hazardous for all shipping modes- USDOT/IATA/IMDG.

UN – none

Marine Pollutant: No

North American Emergency Guide Book – Not applicable

## 15. REGULATORY INFORMATION

The information in this Safety Data Sheet meets the requirements of the United States Occupational Safety and Health Act and regulations promulgated hereunder (29 CFR 1910.1200 ET. SEQ.).

SARA 313 Listing - 40 CFR 372.65 – Silver, Antimony, Nickel, Copper, Zinc, Aluminum, Cobalt

California Prop 65: Warning: This product contains a chemical known to the State of California to cause cancer and birth defects (or other reproductive harm). (Nickel and contains trace amounts of lead not intentionally added)

Ingredients are listed on the TSCA Inventory.  
Contains ingredients that are listed on the New Jersey Right To Know List.

This product has been classified in accordance with the requirements of the Mexican regulations: NOM-018-STPS-2015 and NOM-010-STPS-2014.

This product has been classified in accordance with the hazard criteria of the Canadian Controlled Products Regulation (CPR).

Canadian WHMIS:

Tin, Silver, Copper, Indium, Aluminum, Antimony: Uncontrolled product according to WHMIS classification criteria.

Nickel: D2A Very Toxic Material Causing Other Toxic Effects carcinogenicity: IARC group 2B

D2B Toxic Material Causing Other Toxic Effects skin sensitization in humans

Cobalt: D2A Very Toxic Material Causing Other Toxic Effects carcinogenicity: IARC group 2B; respiratory tract sensitization in humans



D2B Toxic Material Causing Other Toxic Effects skin sensitization in humans

This product has been classified in accordance with the guidelines set by the Dept. of Industrial Health of the Republic of Singapore.

In China:

Decree No. 591: Regulations on the Control over Safety of Hazardous Chemicals

GB 30000.2-29-2013, Rules for classification and labeling of chemicals. (GHS)

GB/T 16483-2008, GB/T 17517-2013

This product has been classified using the Chinese Occupational Limit for Hazardous Agents in the Workplace, GBZ2-2007.

This product has been classified in accordance with: Malaysian – OCCUPATIONAL SAFETY AND HEALTH (CLASSIFICATION, LABELING AND SAFETY DATA SHEET OF HAZARDOUS CHEMICALS) REGULATION OCTOBER 2013 – (CLASS).

Ingredients are listed on the China Chemical Inventory.  
Ingredients are listed on the Korean Existing Chemical Inventory.  
Ingredients are listed on the Philippines Inventory of Chemicals.  
Ingredients are listed on the Canadian Domestic Substance List.



**16. OTHER INFORMATION**

**HMIS Hazard Rating:**

<b>Health:</b>	1
<b>Fire:</b>	1
<b>Reactivity:</b>	0

**Revised Date:** 14 DECEMBER 2017

**Prepared by:** Nancy Swarts, Indium Corporation of America

**Approved by:** Nancy Swarts, Indium Corporation of America

The information and recommendations contained herein are, to the best of The Indium Corporation of America's knowledge and belief, accurate and reliable as of the date issued. The Indium Corporation of America does not warrant or guarantee their accuracy or reliability, and The Indium Corporation of America shall not be liable for any loss or damage arising out of the user thereof. The information and recommendations are offered for the user's consideration and examination, and it is the user's responsibility to satisfy itself that they are suitable and complete for its particular use. If buyer repackages this product, legal counsel should be consulted to insure proper health, safety and other necessary information is included on the container.

**Alloy Table Mixtures****% metal**

Indalloy (Metal Mix)	Tin Sn	Indium In	Germanium Ge	Aluminum Al	Silver Ag	Antimony Sb	Nickel Ni	Zinc Zn	Bismuth Bi	Copper Cu	Cobalt Co	Manganese Mn	RoHS 2* Compliance	Liquidus C/F <sup>0</sup>	Mass Density
121	96.5	-	-	-	3.5	-	-	-	-	-	-	-	YES	221/430	7.36
123	97.5	-	-	-	2.5	-	-	-	-	-	-	-	YES	226/439	7.34
128	100	-	-	-	-	-	-	-	-	-	-	-	YES	232/450	7.28
132	95	-	-	-	5	-	-	-	-	-	-	-	YES	240/464	7.39
133	95	-	-	-	-	5	-	-	-	-	-	-	YES	240/464	7.25
156	90	-	-	-	10	-	-	--	-	-	-	-	YES	295/563	7.51
160	97	-	-	-	--	-	-	-	-	3	-	-	YES	300/572	7.32
173	99	-	1	-	-	-	-	-	-	-	-	-	YES	345/653	7.26
201	91	-	-	-	-	-	-	9	-	-	-	-	YES	199/390	7.27
208	8	-	-	-	7	-	-	-	-	85	-	-	YES	985/1805	8.87
209	65	-	-	-	25	10	-	-	-	-	-	-	YES	233/451	7.80
214	10	-	-	-	60	-	-	-	-	30	-	-	YES	720/1328	9.58
217	5	-	-	-	56	-	-	17	-	22	-	-	YES	650/1202	9.21
221	6	-	-	-	63	-	2.5	-	-	28.5	-	-	YES	800/1472	9.71
226	83.6	8.8	-	-	-	-	-	7.6	-	-	-	-	YES	187/369	7.27
224	46	52.2	-	-	-	--	-	1.8	-	-	-	-	YES	108/226	7.27
232	93.6	-	-	-	4.7	-	-	-	-	1.7	-	-	YES	217/423	7.40
241 (SAC387)	95.5	-	-	-	3.8	-	-	-	-	0.7	-	-	YES	217/423	7.40
243	99	---	-	-	-	-	-	-	-	1	-	-	YES	227/441	7.31
244	99.3	-	-	-	--	-	-	-	-	0.7	-	-	YES	227/441	7.31

246	95.5	-	-	-	4		-	-	-	0.5	-	-	YES	217/423	7.40
251	96.2	--	-	-	2.5	0.5	--	-	-	0.8	-	-	YES	217/423	7.37
252	95.5	-	-	-	3.9	-	-	-	-	0.6	-	-	YES	217/423	7.40
256 (SAC305)	96.5	-	-	-	3	-	-	-	-	0.5	-	-	YES	218/424	7.40
258 (SAC105)	98.5	-	-	-	1	-	-	-	-	0.5	-	-	YES	227/441	7.32
259	90					10							YES	248/478	7.25
<b>Indalloy (Metal Mix)</b>	<b>Tin Sn</b>	<b>Indium In</b>	<b>Germanium Ge</b>	<b>Aluminum Al</b>	<b>Silver Ag</b>	<b>Antimony Sb</b>	<b>Nickel Ni</b>	<b>Zinc Zn</b>	<b>Bismuth Bi</b>	<b>Copper Cu</b>	<b>Cobalt Co</b>	<b>Manganese Mn</b>	<b>RoHS 2* Compliance</b>	<b>Liquidus C/F<sup>0</sup></b>	<b>Mass Density</b>
Non Standard Sn995 (Cobalt 995)	99.5	-	-	-	-	-	-	-	-	0.5	<500 ppm	-	YES	-	7.29
263 (SAC 0307)	99	-	-	-	0.3	-	-	-	-	0.7	-	-	YES	227/441	7.31
270	90.95	-	-	-	3.8	1.4	0.15	-	3	0.7	-	-	YES		
271	88.9	-	-	-	3.8	6	-	-	0.3	1	-	-	YES		
272	90	-	-	-	3.8	3.5	-	-	1.5	1.2	-	-	YES		7.39
276	90.6	-	-	-	3.2	5.5	-	-		0.7	-	-	YES		7.32
	<b>NON STANDARD/OTHER ALLOY MIXTURES</b>														
Non Standard	27	-	-	-	73	-	-	-	-	-	-	-	YES	-	9.38
Non Standard	30	65	-	-	4.5	-	-	-	-	0.5	-	-	YES	-	7.41
Non Standard	33.7	66.3	-	-	-	-	-	-	-	-	-	=	YES	-	7.29
Non Standard	54	40	-	-	2	-	-	-	-	4	-	=	YES	-	7.39
Non Standard	61	-	-	-	-	-	-	-	-	39	-	=	YES	-	7.85
Non Standard	63.5	-	-	-	25	10	-	-	-	1.5	-	=	YES	-	7.82
Non Standard	64	30	-	-	2	-	-	-	-	4	-	=	YES	-	7.39
Non Standard	65	-	-	-	25	10	-	-	-	-	-	=	YES	-	7.80

Non Standard	74	20	-	-	2	-	-	-	-	4	-	=	YES	-	7.38
Non Standard	78	-	-	-	2.5	-	-	-	19.5	-	-	-	YES	-	7.73
Non Standard	78.4	9.8	-	-	2	-	-	-	9.8	-	-	-	YES	-	7.52
Non Standard	78.5	-	-	-	10	10	-	-	-	1.5	-	-	YES	-	
Non Standard	80	-	-	-	10	10	-	-	-	-	-	-	YES	-	
Non Standard	82	-	-	-	18	-	-	-	-	-	-	-	YES	295/563	7.71
Non Standard	82	-	-	-	18	-	-	-	-	-	-	-	YES	295/563	7.71
Non Standard	84	10	-	-	2	-	-	-	-	4	-	=	YES	-	7.38
Non Standard	85	-	-	-	-	15	-	-	-	-	-	-	YES	300/572	7.31
Non Standard	85.9	10	-	-	3.1	-	-	-	-	1	-	-	YES	200/393	7.37
Non Standard	88	-	-	-	-	-	-	-	-	12	-	-	YES	-	7.45
Indalloy (Metal Mix)	Tin Sn	Indium In	Germanium Ge	Aluminum Al	Silver Ag	Antimony Sb	Nickel Ni	Zinc Zn	Bismuth Bi	Copper Cu	Cobalt Co	Manganese Mn	RoHS 2* Compliance	Liquidus C/F <sup>0</sup>	Mass Density
Non Standard	88	-	-	-	12	-	-	-	-	-	-	-	YES	-	7.56
Non Standard Ribbon	89	-	-	-	-	10.5	-	-	-	0.5	-	-	YES	-	7.21
Non Standard	89	2.5	-	-	3.8	3.5	-	-	0.5	0.7	-	-	Yes	-	7.36
Non Standard	89.1	-	-	-	3.8	5.8	-	-	0.3	1	-	-	YES	-	7.34
Non Standard	89.3	0.5	-	-	3.8	5.5	-	-	-	0.9	-	-	YES	-	7.34
Non Standard	91	-	-	0.06	-	-	-	8.94	-	-	-	-	YES	-	7.26
Non Standard	91.25	-	-	-	-	-	-	8.75	-	-	-	-	YES	199/390	7.27
Non Standard	91.25	-	-	--	2.25	-	-	-	6.0	0.5	-	=	YES	-	7.45
Non Standard	91.5	-	-	-	-	8.5	-	-	-	-	-	=	YES	-	7.22
Non Standard	91.98	-	0.02	-	-	8	-	-	-	-	-	=	YES	-	7.22

Non Standard	92	-	-	-	-	-	-	8	-	-	-	-	YES	-	7.27
Non Standard	92.4	-	-	-	-	7	0.1	-	-	0.5	-	-	YES	-	7.24
Non Standard	92.5	-	-	-	3.5	-	-	-	-	4	-	-	YES	-	7.41
Non Standard	93	-	-	-	-	-	-	--	-	7	-	-	YES	-	7.32
Non Standard	93.5	-	-	-	3.5	-	-	-	3	-	-	-	YES	-	7.42
Non Standard	94	3	-	-	2.5	-	-	-	-	0.5	-	-	YES	-	7.34
Non Standard IPN 52357	94.13	-	-	0.05	1.63	0.61	-	0.75	-	2.87	-	-	YES	-	7.34
Non Standard	94.8	-	-	-	3.8	-	-	0.7	-	0.7	-	-	YES	-	7.37
Non Standard Solder Wire IPN 52361	94.95	-	-	0.05	-	1.35	-	3.65	-	-	-	-	YES	-	7.25
Non Standard	94.98	-	0.02	-	-	5	-	-	-	-	-	-	YES	-	7.24
Non Standard	95	-	-	-	3.8	-	-	0.5	-	0.7	-	-	YES	-	7.37
<b>Indalloy (Metal Mix)</b>	<b>Tin Sn</b>	<b>Indium In</b>	<b>Germanium Ge</b>	<b>Aluminum Al</b>	<b>Silver Ag</b>	<b>Antimony Sb</b>	<b>Nickel Ni</b>	<b>Zinc Zn</b>	<b>Bismuth Bi</b>	<b>Copper Cu</b>	<b>Cobalt Co</b>	<b>Manganese Mn</b>	<b>RoHS 2* Compliance</b>	<b>Liquidus C/F<sup>0</sup></b>	<b>Mass Density</b>
Non Standard	95	1.5	-	-	3.5	-	-	-	-	-	-	-	YES	-	7.36
Non Standard	95	-	-	0.5	4	-	-	-	-	0.5	-	-	YES	-	7.31
Non Standard	95.4	-	-	-	3.8	-	-	0.1	-	0.7	-	-	YES	-	7.37

Non Standard	95.5	-	-	-	3.5	-	-	-	-	1	-	-	YES	218/424	7.40
Non Standard	95.5	-	-	-	3.65	-	-	-	0.15	0.7	-	-	YES	-	7.38
Non Standard Doped with 0.05% Al	95.5	-	-	-	4.0	-	-	-	-	0.5	-	-	YES	-	7.40
Non Standard	95.7	-	-	-	3.4	-	-	-	-	0.9	-	-	YES	218/424	7.36
SAC357	95.8	-	-	-	3.5	-	-	-	-	0.7	-	-	YES	-	7.37
Non Standard	95.9	-	-	-	3.4	-	-	-	-	0.7	-	-	YES	218/424	7.40
Non Standard	95.9	1	-	-	0.1	-	-	-	-	3	-	-	YES	-	7.32
Non Standard	96	-	-	-	4	-	-	-	-	-	-	-	YES	240/465	7.40
Non Standard	96.3	-	-	-	3	-	-	-	-	0.7	-	-	YES	218/424	7.40
Non Standard	96.3	-	-	-	3.7	-	-	-	-	-	-	-	YES	221/430	7.42
Non Standard	96.3	-	-	-	3.2	-	-	-	-	0.5	-	-	YES	218/424	7.38

Non Standard	96.5	-	-	-	3	-	-	-	-	0.5	-	-	YES	218/424	7.40
Non Standard	97	-	-	-	2.5	-	-	-	-	0.5	-	-	YES	-	7.34
Non Standard (SAC 209)	97.1	-	-	-	2.0	-	-	-	-	0.9	-	-	YES	-	7.34
<b>Indalloy (Metal Mix)</b>	<b>Tin Sn</b>	<b>Indium In</b>	<b>Germanium Ge</b>	<b>Aluminum Al</b>	<b>Silver Ag</b>	<b>Antimony Sb</b>	<b>Nickel Ni</b>	<b>Zinc Zn</b>	<b>Bismuth Bi</b>	<b>Copper Cu</b>	<b>Cobalt Co</b>	<b>Manganese Mn</b>	<b>RoHS 2* Compliance</b>	<b>Liquidus C/F<sup>0</sup></b>	<b>Mass Density</b>
Non Standard Solder Wire	97.5	-	-	-	1.5	-	-	-	-	0.7	0.3	-	YES	-	7.19
Non Standard Doped with 0.02% Titanium	97.5	-	-	-	1.8	-	-	-	-	0.7	-	-	YES	-	7.33
Non Standard	97.7	-	-	-	2	-	0.3	-	-	-	-	-	YES	-	7.19
Non Standard	97.9	-	-	-	2	-	0.1	-	-	-	-	-	YES	-	7.28
Non Standard	98	-	-	-	2	-	-	-	-	-	-	-	YES	-	7.32
Non Standard	98.13	-	-	-	1.1	-	-	-	-	0.65	-	≤0.15	YES	-	7.26
Non Standard Doped with 0.02% Titanium	98.3	-	-	-	1.0	-	-	-	-	0.7	-	-	YES	-	7.31
<b>Indalloy (Metal Mix)</b>	<b>Tin Sn</b>	<b>Indium In</b>	<b>Germanium Ge</b>	<b>Aluminum Al</b>	<b>Silver Ag</b>	<b>Antimony Sb</b>	<b>Nickel Ni</b>	<b>Zinc Zn</b>	<b>Bismuth Bi</b>	<b>Copper Cu</b>	<b>Cobalt Co</b>	<b>Manganese Mn</b>	<b>RoHS 2* Compliance</b>	<b>Liquidus C/F<sup>0</sup></b>	<b>Mass Density</b>
Non Standard Doped with 0.04% Mn and 0.01 Ce	98.45	-	-	-	1	-	-	-	-	0.5	-	0.04	YES	-	7.31
Non Standard (SAC 105)	98.5	-	-	-	1	-	-	-	-	0.5	-	-	YES	-	7.31
Non Standard (SAC 105) Doped with 0.05%	98.5	-	-	-	1	-	-	-	-	0.5	-	Doped 0.05	YES	-	7.31

Manganese															
Non Standard (SACM0510) Doped with .02% - .06% Manganese	98.5	-	-	-	0.5	-	-	-	-	1.0	-	Doped .02 - .06	YES	-	7.31
Non Standard (SAC 105) Doped with 0.05% Manganese and 0.02% Cerium	98.5	-	-	-	1	-	-	-	-	0.5		Doped 0.05	YES	-	7.31
Non Standard (SAC# 0307)	99	-	-	-	0.3	-	-	-	-	0.7	-	-	YES	-	7.30
Non Standard	99.1	-	-	-	-	-	-	-	-	0.9	-	-	YES	-	7.29
Non Standard	99.15	-	-	-	-	-	-	-	0.3	0.5	0.05	-	YES		7.29
Non Standard Sn992	99.2	-	-	-	-	-	-	-	0.3	0.5	<500 ppm	-	YES	-	7.29
Non Standard	99.3	-	-	-	-	-	-	-	-	0.7	-	-	YES	-	7.29
Non Standard	95	-	-	-	-	-	-	-	-	5	-	-	YES	-	7.35
Non Standard	95	=	=	=	0.5	=	=		-	4.5	=	=	YES	-	7.37

Other mixtures are available that fall under the non- standard mixtures of the above metals.

\*RoHS 2 = Restriction on Hazardous Substances (2011/65/EU)