

Product Data Sheet

2205 Rosin Flux

Features

- Meets J-STD-003/002 specifications for flux type 1
- Non-corrosive residue

Introduction

2205 Rosin Flux is an alcohol-based flux that is ideal for soldering all surface finishes. It can be used to test solderability according to IPC J-STD-003 and IPC J-STD-002.

Process Recommendations

2205 Rosin Flux can be applied by wave or dipping. If thinning is required, use 16-1000 Flux Thinner to maintain specific gravity during use.

Physical Properties

Test	2205	16-1000
Color	Amber	Clear
Specific Gravity @15.5° C (60° F) @25° C (77° F)	0.848 0.843	0.788 0.783
Acid Value	39	0
Solids Content	26.40	0
Flash Point	12° C (54° F)	12° C (54° F)
IPC J-STD-004 Flux Type	ROL1	NA

All information is for reference only. Not to be used as incoming product specifications.

IPC Surface Insulation Resistance

Test Pattern IPC B24		24 Hr	96 Hr	168 Hr
	Control	1.23E+10	5.36E+09	4.60E+09
	Pattern Up	8.49E+09	4.42E+09	4.80E+09
	Pattern Down	1.98E+10	9.37E+09	9.35E+09

Packaging

- 1-gallon containers
- 5-gallon containers

Technical and Customer Support

Indium Corporation's internationally experienced engineers provide in-depth technical assistance to our customers. Thoroughly knowledgeable in all facets of Material Science as it applies to the electronics and semiconductor sectors, Technical Support Engineers provide expert advice in solder properties, alloy compatibility, and selection of solder preforms, wire, ribbon, and paste. Indium Corporation's Technical Support engineers provide rapid response to all technical inquiries.

Safety Data Sheets

The SDS for this product can be found online at <http://www.indium.com/sds>

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

Form No. 98669 R1

www.indium.com

askus@indium.com

ASIA: Singapore, Cheongju: +65 6268 8678
 CHINA: Suzhou, Shenzhen: +86 (0)512 628 34900
 EUROPE: Milton Keynes, Torino: +44 (0) 1908 580400
 USA: Utica, Clinton, Chicago, Rome: +1 315 853 4900



©2014 Indium Corporation

ISO 9001
REGISTERED