

## PRODUCT DATA SHEET

# Nitinol Soldering Kit

### Contents

- Indalloy®121 (96.5Sn/3.5Ag 0.030") solder wire
- Indalloy® Flux #2
- Nitinol #1 wire 0.017"

**Nitinol** requires a strong flux to remove surface oxides to facilitate wetting of the solder to the surface.

### Indalloy® Flux #2

Indalloy® Flux #2 is a specialty, acid-based flux formulated for soldering **Nitinol**. It also works on high chromium-containing alloys including stainless steel.

Indalloy® Flux #2 is compatible with all types of solders. It can be brushed on, dispensed, or sprayed. All application equipment should be acid-resistant. It is not recommended for electronics applications.

### Cleaning

Flux residue removal is mandatory and may be accomplished by means of warm water and mechanical scrubbing. Cleaning should be performed as soon as possible after the soldering operation to avoid corrosion. The cleaning water temperature should not exceed 50°C. Excessive water temperature may cause secondary reactions and result in corrosion and/or pitting. A warm water sonication may also be a means of flux residue removal.



### Flux Technical Specifications

	Flux #2 (P/N 84002)
Activation Range	100–371°C
Specific Gravity	1.53gm/cc
Flash Point	Non-flammable
Chloride Content	No zinc or other heavy metal chlorides
pH	1–1.5
Appearance	Water white
Cleaning	Warm water (<50°C) and mechanical scrubbing
Shipping	Transport in accordance with applicable regulations and requirements

From One Engineer To Another®



## PRODUCT DATA SHEET

# Nitinol Soldering Kit

### Nitinol Wire Specifications

	Nitinol #1	
Austenitic Finish Temperature (Af)	10–18°C	
Flash Point	Non-flammable	
Chemical Composition	Element	Weight %
	Nickel	54.5 to 57.0 (Ref.)
	Titanium	Balance
	Carbon	<0.05 (500ppm max.)
	Cobalt	<0.05 (500ppm max.)
	Copper	<0.01 (100ppm max.)
	Chromium	<0.01 (100ppm max.)
	Hydrogen	<0.005 (50ppm max.)
	Iron	<0.03 (300ppm max.)
	Niobium	<0.025 (250ppm max.)
	Oxygen	<0.05 (500ppm max.)
	Any Single Trace Element	<0.1
	Total Trace Elements	<0.25
Ultimate Tensile Strength	>180,000psi	
Appearance	Shiny, light brown color	
Cleaning	Alcohol wipe	
Shipping	Transport in accordance with applicable regulations and requirements	

Nitinol courtesy of Fort Wayne Metals.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

All of Indium Corporation's solder paste and preform manufacturing facilities are IATF 16949:2016 certified. Indium Corporation is an ISO 9001:2015 registered company.

Contact our engineers: [askus@indium.com](mailto:askus@indium.com)

Learn more: [www.indium.com](http://www.indium.com)

ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900



©2023 Indium Corporation