

## Product Data Sheet

# TACFlux® RMA-155

### Introduction

**TACFlux® RMA-155** is a RMA flux formulated for SnAgCu and SnAg solders (also compatible with SnPb solder). **TACFlux® RMA-155** provides excellent wetting in air or nitrogen atmospheres. The flux and flux residue are halogen-free.

### Properties

J-STD-004 (IPC-TM-650)	
Test	Result
Flux Type Classification	R0L0
Flux Induced Corrosion (Copper Mirror)	Type L
Presence of Halide: Silver Chromate Fluoride Spot test Cl Equivalent	Pass Pass <0.0%
Post Reflow Flux Residue (ICA Test)	~35%
SIR	Pass
Bellcore Electromigration	Pass
Viscosity (C & P)*	10kcps
Tack	120g
QQ-S-571F	Meets or exceeds

\*Cone & Plate viscosity @ 5 minutes.

Additional Test Results	
Appearance	Light Yellow-Amber
Maximum Reflow Temperature	260°C
Reflow Atmosphere	Nitrogen or Air
Shelf Life	1 year
Storage Condition	Stored @ 0-30°C (tip down for syringe or cartridge)

All information is for reference only. Not to be used as incoming product specifications.

### Packaging

**TACFlux® RMA-155** is available in 10cc and 30cc syringes or 100g jars. Other packaging can be provided to meet specific requirements.

### Cleaning

**TACFlux® RMA-155** is designed for RMA applications. If necessary, the flux can be removed by using a commercially available flux cleaner.

### Reflow

Peak reflow temperature should be <260°C in an air or nitrogen atmosphere.

### Storage

**TACFlux® RMA-155** syringes and cartridges should be stored tip down at 0°-30°C. If refrigerated, **TACFlux® RMA-155** should be thawed for 4 hours at room temperature before using.



### Technical Support

Indium Corporation's internationally experienced engineers provide in-depth technical assistance to our customers. Thoroughly knowledgeable in all facets of Material Science as it applies to the electronics and semiconductor sectors, Technical Support Engineers provide expert advice in solder properties, alloy compatibility, and selection of solder preforms, wire, ribbon, and paste. Indium Corporation Technical Support engineers provide rapid response to all technical inquiries.

### Safety Data Sheets

The SDS for this product can be found online at <http://www.indium.com/sds>

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

Form No. 98993 R0

[www.indium.com](http://www.indium.com)

[askus@indium.com](mailto:askus@indium.com)

ASIA: Singapore, Cheongju: +65 6268 8678  
 CHINA: Suzhou, Shenzhen: +86 (0)512 628 34900  
 EUROPE: Milton Keynes, Torino: +44 (0) 1908 580400  
 USA: Utica, Clinton, Chicago, Rome: +1 315 853 4900



©2014 Indium Corporation

ISO 9001  
REGISTERED