

Product Data Sheet

Wave Solder Flux #1010 Water-Soluble

Features

- Non-flammable
- High activity
- Wide process window
- Use with Pb-Free and Sn-Pb assembly processes

Introduction

Wave Solder Flux #1010 is a versatile VOC-Free water-soluble wave flux that provides excellent solderability on difficult to solder assemblies.

Wave Solder Flux #1010 is biodegradable and cleans to low ionic levels, leaving the assembly with high surface insulation resistance (SIR).

Process Recommendations

Wave Solder Flux #1010 should be applied by ultrasonic spray for best results. Topside board temperatures can range from 100°C to 150°C (300°F) depending on equipment capability and assembly requirements. Preheat temperature should be adjusted to ensure complete water removal before contact with the solder wave.

A thin uniform flux deposition of 500-1,000 micrograms per square inch of flux solids should be applied as a starting point.

Because **Wave Solder Flux #1010** is water-based, it does not require frequent acid value monitoring. If thinning is required, deionized water should be used.

Wave Solder Flux #1010 may freeze if exposed to temperatures below 0°C (32°F). If the flux becomes frozen, bring to room temperature until thawed and agitate. The material is not affected by freezing.

Flux residue cleans best in water 120-140°F. A final in deionized water will produce the best results.

Physical Properties

Test	Result
Color:	Clear
Specific Gravity:	
@25°C (77°F)	1.055
@15.5°C (60°F)	1.058
Solids Content	20%
Flash Point (°F TCC)	None
J-STD-004A Flux Type	ORH1

All information is for reference only. Not to be used as incoming product specifications.

Packaging

- 5 gallon containers
- 55 gallon drums

Technical Support

Indium Corporation's internationally experienced engineers provide in-depth technical assistance to our customers. Thoroughly knowledgeable in all facets of Material Science as it applies to the electronics and semiconductor sectors, Technical Support Engineers provide expert advice in solder properties, alloy compatibility and selection of solder preforms, wire, ribbon and paste. Indium Corporation's Technical Support engineers provide Rapid Response to all technical inquiries.

Material Safety Data Sheet

The MSDS for this product can be found online at <http://www.indium.com/techlibrary/msds.php>

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products

described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices.

Form No. 97936 R2

S O L D E R

INDIUM CORPORATION®

www.indium.com
askus@indium.com
PRC +86 (0)512 628 34900
SINGAPORE +65 6268 8678
UK +44 (0) 1908 580400
USA +1 315 853 4900



ISO 9001
REGISTERED