INDIUM CORPORATION®

PRODUCT DATA SHEET

Gallium Sesquioxide (Ga₂O₃)

Synonyms	Gallium Oxide, Gallium (III) Oxide		
CAS Number	12024-21-4		
EC Number	234-691-7		
RTECS	LW9650000		
Purity	99.99 to 99.999%		
Appearance/Form	White powder		
Crystal Structure	Mostly β-phase, confirmed by XRD		
Formula Weight	187.44 g/mol		
Theoretical Gallium Content	74.39%		
Density	6.44 g/cm ³ ; approx. 0.7 g/cm ³ apparent		
Melting Point	1900°C		
Vapor Pressure	N/A		
Solubility	Soluble in alkalis, slightly in hot acids, insoluble in water		

Impurities	99.99 (Type 1 or 2)		99.999 (Type 1)	
	Typical	Maximum	Typical	Maximum
Moisture (LOD, 104°C)	<0.1%	0.1%	<0.1%	0.1%
Volatile (LOI, 800°C)	<0.1%	0.1%	<0.1%	0.1%
Aluminum (Al)	< 5.0 ppm	5.0 ppm	< 1.0 ppm	3.0 ppm
Arsenic (As)	< 1.0 ppm	2.0 ppm	< 1.0 ppm	1.0 ppm
Calcium (Ca)	< 10.0 ppm	10.0 ppm	< 1.0 ppm	3.0 ppm
Chromium (Cr)	< 3.0 ppm	5.0 ppm	< 1.0 ppm	1.0 ppm
Copper (Cu)	< 3.0 ppm	5.0 ppm	< 1.0 ppm	1.0 ppm
Germanium (Ge)	< 5.0 ppm	5.0 ppm	< 1.0 ppm	3.0 ppm
Iron (Fe)	< 5.0 ppm	5.0 ppm	< 1.0 ppm	3.0 ppm
Indium (In)	< 5.0 ppm	5.0 ppm	< 1.0 ppm	3.0 ppm
Magnesium (Mg)	< 3.0 ppm	5.0 ppm	< 1.0 ppm	1.0 ppm
Nickel (Ni)	< 1.0 ppm	5.0 ppm	< 1.0 ppm	1.0 ppm
Lead (Pb)	< 1.0 ppm	2.0 ppm	< 1.0 ppm	1.0 ppm
Silicon (Si)	< 3.0 ppm	10.0 ppm	< 1.0 ppm	3.0 ppm
Sodium (Na)	< 10.0 ppm	10.0 ppm	< 1.0 ppm	3.0 ppm
Tin (Sn)	< 3.0 ppm	5.0 ppm	< 1.0 ppm	1.0 ppm
Zinc (Zn)	< 3.0 ppm	5.0 ppm	< 1.0 ppm	1.0 ppm
Total Combined Metals	< 50 ppm	< 100 ppm	< 10 ppm	< 10 ppm

All information is for reference only. Not to be used as incoming product specifications.

www.indium.com askus@indium.com


ASIA: Singapore, Cheongju, Malaysia: +65 6268 8678 CHINA: Suzhou, Shenzhen: +86 (0)512 628 34900 EUROPE: Milton Keynes, Torino: +44 (0) 1908 580400 USA: Utica, Clinton, Chicago, Rome: +1 315 853 4900



ISO 9001 REGISTERED

INDIUM CORPORATION[®]


Gallium Sesquioxide (Ga₂O₃)



Type 1 - Rod shaped uniform particles.

Typical Particle Size and Surface Area Analysis

	d90 (micron)	d50 (micron)	d10 (micron)	BET (m²/g)
Type 1	2.5-4.0	1.25-2.25	0.75-1.25	12-17
Type 2	20-45	5-15	1-5	12-17



Type 2 – Agglomerates of smaller amorphous particles.

Packaging

PE Bottle: 100g, 500g, 1kg, 2kg Plastic Pail: 5kg, 10kg, 20kg Plastic Drum: 25kg, 50kg and up

Applications

- Phosphors
- · Cathodes for solid oxide fuel cells
- Piezo-electric crystals
- GGG crystals and IGZO targets for latest technology displays

Storage and Shelf Life

Gallium Sesquioxide should be stored at room temperature and the container kept tightly sealed. Shelf life is 12 months.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

www.indium.com askus@indium.com

ASIA: Singapore, Cheongju, Malaysia: +65 6268 8678 CHINA: Suzhou, Shenzhen: +86 (0)512 628 34900 EUROPE: Milton Keynes, Torino: +44 (0) 1908 580400 USA: Utica, Clinton, Chicago, Rome: +1 315 853 4900



