

PRODUCT DATA SHEET

NC-771 Pb-Free, No-Clean Flux

Features

- Passes SIR test in the un-reflowed state
- Halogen-free
- Backwards compatible with eutectic SnPb
- Ideal for high-reliability electronic circuitry
- Benign, non-sticky, post reflow residue
- Provides excellent wetting
- Wide reflow process window



Introduction

NC-771 is a halogen-free, low-residue, all-purpose liquid flux that passes the SIR test in the un-reflowed state. It can be used in a standard SnPb or Pb-free rework or soldering process. In addition to the aesthetic benefits, the ultra-low post reflow residue is non-tacky and will not interfere with probe testing.

Process Recommendations

NC-771 is a multi-purpose flux that can be used in an SMT rework process or almost any soldering application that requires the addition of a liquid flux. Typical application methods include a flux pen that allows you to apply a precise amount of flux to the solder joint. It can also be sprayed on for use in a selective soldering process or dispensed from a flux bottle. Care should be taken not to flood the solder joint and to apply the flux only to areas that will be exposed to complete heating from the solder iron or rework tool.

NC-771 is designed for no-clean applications. However, the flux can be removed if necessary by using a commercially available flux remover.

Physical Properties

Test	Result
Color	Clear
Flash Point (°F TCC)	12
Smell	Alcoholic

Packaging

NC-771 can be supplied in flux pens or in plastic containers.

Shelf Life

1 year from DOM when stored at 0–30°C

Safety Data Sheets

The SDS for this product can be found online at <http://www.indium.com/sds>

Technical Support

Indium Corporation sets the industry standard in providing rapid response, on-site technical support for our customers worldwide. Indium Corporation's team of Technical Support Engineers can provide expertise in all aspects of materials science and semiconductor packaging process applications.

J-STD-004A TESTING RESULTS

Test	Result
• Flux Type Classification	ORLO
• SIR	Pass
• Copper Mirror	Type L
• Silver Chromate	Pass
• Fluoride Spot Test	Pass
• Corrosion	Pass
• Acid Value (nominal)	32.5 mg KOH/gm
• Specific Gravity (nominal)	0.825
• Flux Solids (typical)	5.0%

All information is for reference only. Not to be used as incoming product specifications.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

Form No. 97675 (A4) R6

www.indium.com

askus@indium.com

ASIA: Singapore, Cheongju, Malaysia: +65 6268 8678
 CHINA: Suzhou, Shenzhen: +86 (0)512 628 34900
 EUROPE: Milton Keynes, Torino: +44 (0) 1908 580400
 USA: Utica, Clinton, Chicago, Rome: +1 315 853 4900



ISO 9001
REGISTERED