

PRODUCT DATA SHEET

Wave Solder Flux 3592

No-Residue

Introduction

3592 Wave Soldering Flux is a low-solids, rosin-/resin-free flux designed to leave a no-residue appearance. This flux contains very effective flux activators that provide excellent solderability and reduced defects on surface mount, through-hole, and mixed-technology assemblies.

3592 Wave Soldering Flux can be used with common board finishes, including HASL, Immersion Ag, ENIG, OSP, and other alternative coatings to provide excellent through-hole penetration resulting in better topside solder fillets.

Features

- Rosin-/resin-free with ultra-low residue appearance
- Low residue won't interfere with probe testing requirements
- Can be conformal coated without cleaning
- Meets IPC and Bellcore reliability specifications

Process Recommendations

3592 Wave Soldering Flux is best applied by ultrasonic spray. For best results, the following guidelines should be adhered to:

- In spray applications, a thin uniform flux deposition of 500–1,000 micrograms of flux solids per square inch should be applied as a starting point.
- Flux application variables, including flux deposition and uniformity, are integral factors when soldering with a no-clean chemistry. Topside board temperature should be approximately 93–104°C (200–220°F). Preheat temperatures can differ based on wave soldering equipment, fluxes, board thickness, components, and conveyor speed.

Physical Properties

Test	Result	
	3592	16-3000
Color	Clear	Clear
Specific Gravity at 25°C (77°F) at 15.5°C (60°F)	0.820	0.783
	0.826	0.790
Acid Value	22.0	0
Solids Content	3.0	0
Flash Point (°F TCC)	54	54
J-STD-004 Flux Type	ORLO	N/A
Shelf Life	2 years from DOM	N/A

Packaging

- 5-gallon containers
- 55-gallon drums

Safety

All fluxes with low flash points should be handled with caution. Store in a dry, well-ventilated area away from sparks, flames, and direct heat. Consult the Safety Data Sheet for full details.

Technical Support

Indium Corporation's internationally experienced engineers provide in-depth technical assistance to our customers. Thoroughly knowledgeable in all facets of Material Science as it applies to the electronics and semiconductor sectors, Technical Support Engineers provide expert advice in solder properties, alloy compatibility and selection of solder preforms, wire, ribbon, and paste. Indium Corporation's Technical Support Engineers provide rapid response to all technical inquiries.

Safety Data Sheet

The SDS for this product can be found online at www.indium.com/sds

From One Engineer To Another®



PRODUCT DATA SHEET

Wave Solder Flux 3592

No-Residue

Bellcore Surface Insulation Resistance Test

Test Pattern	Boards	Initial Reading*	Final Reading*
Standard Bellcore	Control	2.89×10^{13}	1.88×10^{13}
	Pattern up	3.92×10^{11}	3.78×10^{11}
	Pattern down	1.18×10^{13}	1.12×10^{13}

Bellcore Electromigration Resistance Test

Test Pattern	Boards	Initial Reading*	Final Reading*
IPC-B25A	Control	6.51×10^{11}	3.01×10^{11}
	Pattern up	6.99×10^9	5.29×10^9
	Pattern down	1.04×10^9	5.18×10^9

IPC Surface Insulation Resistance Test

Test Pattern	Boards	24 Hours*	96 Hours*	168 Hours*
IPC-B25A	Control	1.81×10^{10}	9.96×10^9	7.55×10^9
	Pattern up	1.25×10^{10}	6.53×10^9	5.31×10^9
	Pattern down	1.15×10^{10}	7.36×10^9	6.78×10^9

*All readings expressed in Ohms

All information is for reference only.

Not to be used as incoming product specifications.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

Contact our engineers today: askus@indium.com

Learn more: www.indium.com



ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900



©2018 Indium Corporation