

PRODUCT DATA SHEET

NC-SMQ® 51SC

Solder Paste

Introduction

NC-SMQ® 51SC is an air reflow, no-clean solder paste designed for use in a wide range of environmental conditions. It has exceptional stencil life and tack strength, and offers consistent print definition even in ultra-fine pitch applications. **NC-SMQ® 51SC's** wide processing window allows it to be used with standard eutectic SnPb, SnPbAg, SnAgCu, and high-temperature alloys including AuSn, SnPb, and SnPbAg.

Features

- Wide reflow process window
- Consistent fine pitch print deposition
- Extended open time
- Superior tack strength
- No-clean residue
- Exceptional wetting in air reflow

Storage and Handling Procedures

Refrigerated storage will prolong the shelf life of solder paste. Solder paste packaged in cartridges should be stored tip down.

Storage Conditions (unopened containers)	Shelf Life
<10°C	6 months

Solder paste should be allowed to reach ambient working temperature prior to use. Generally, paste should be removed from refrigeration at least two hours before use. Actual time to reach thermal equilibrium will vary with container size. Paste temperature should be verified before use. Jars and cartridges should be labeled with date and time of opening.

Cleaning

NC-SMQ® 92J is designed for no-clean applications. However, the flux can be removed if necessary by using a commercially available flux residue remover. Stencil cleaning is best performed using isopropyl alcohol (IPA) as a solvent. Most commercially available non-water-based stencil cleaners work well.

Safety Data Sheets

The SDS for this product can be found online at <http://www.indium.com/sds>

OVER→

Alloys

Indium Corporation manufactures low-oxide spherical solder powder composed of SnPb and SnPbAg in a standard type 3 mesh size (J-STD-006). Other non-standard mesh sizes are available upon request. The weight ratio of the solder powder to solder paste is referred to as the metal load and is typically in the range of 82-91% for standard alloy compositions.

Standard Product Specifications

Alloy	Metal Load (% by weight)		Powder Type
	Printing	Dispensing	
Sn63	90-90.5	87	Type 3
Sn62	90-90.5	87	
SAC305	89	84	

Compatible Products

- Rework Flux: PoP Flux 8.9HF-LV, TACFlux® 007
- Cored Wire: CW-807
- Wave Flux: WF-9945, WF-9955, FP-500, NC-771

Note: Other products may be applicable. Please consult one of Indium Corporation's Technical Support Engineers.

BELLCORE AND J-STD TESTS & RESULTS

Test	Result	Test	Result
J-STD-004 (IPC-TM-650)		J-STD-005 (IPC-TM-650)	
• Flux Type Classification	ROL1	• Typical Solder Paste Viscosity (Sn63/Pb37, Type 3)	
• Flux Induced Corrosion (Copper Mirror)	Pass	• Brookfield (5 rpm)	
• Presence of Halide:		• 90% Metal Load	850 kcps
• Silver Chromate	Pass	• 90.5% Metal Load	1100 kcps
• Fluoride Spot Test	Pass	• Malcom (10 rpm)	
• Cl Equivalent	<0.019% of paste	• 90% Metal Load	1800 poise
• Post Reflow Flux Residue (ICA Test)	47%	• Typical Thixotropic Index; SSF	-0.60
• Corrosion	Pass	• Slump Test	Pass
• SIR	Pass	• Solder Ball Test	Pass
• Typical Acid Value	85	• Typical Tackiness	38 grams
		• Wetting Test	Pass
		• Bellcore Electromigration	Pass

All information is for reference only. Not to be used as incoming product specifications.

Form No. 97538 R13

www.indium.com

askus@indium.com

ASIA: Singapore, Cheongju, Malaysia: +65 6268 8678
 CHINA: Suzhou, Shenzhen: +86 (0)512 628 34900
 EUROPE: Milton Keynes, Torino: +44 (0) 1908 580400
 USA: Utica, Clinton, Chicago, Rome: +1 315 853 4900



©2016 Indium Corporation

ISO 9001
REGISTERED

NC-SMQ® 51SC Solder Paste

Printing



Stencil Design:

Electroformed and laser cut/electropolished stencils produce the best printing characteristics among stencil types. Stencil aperture design is a crucial step in optimizing the print process. The following are a few general recommendations:

- Discrete components — A 10–20% reduction of stencil aperture has significantly reduced or eliminated the occurrence of mid-chip solder beads. The “home plate” design is a common method for achieving this reduction.
- Fine pitch components — A surface area reduction is recommended for apertures of 20 mil pitch and finer. This reduction will help minimize solder balling and bridging that can lead to electrical shorts. The amount of reduction necessary is process dependent (5–15% is common).
- For optimum transfer efficiency and release of the solder paste from the stencil apertures, industry standard aperture and aspect ratios should be adhered to.

Reflow

Recommended Profile:



Printer Operation	
Solder Paste Bead Size	~20-25mm in diameter
Print Speed	25-50mm/second
Squeegee Pressure	0.018-0.027Kg/mm of blade length
Underside Stencil Wipe	Start at once per every 10-25 prints and decrease frequency until optimum value is reached
Squeegee Type/Angle	Metal with appropriate length / ~45-60 degrees
Separation Speed	5-20mm/second or per equipment manufacturer's specifications
Solder Paste Stencil Life	>8 hrs. (at 30-60% RH and 22-28°C)

Note: All parameters are for reference only. Modifications may be required to fit process and design.

Profile Details	Parameters			Comments
	SAC305	SAC305/Sn63/Sn62	Sn63/Sn62	
Ramp Profile (Average Ambient to Peak) - Not the Same as Maximum Rising Slope	0.5-1°C/Second Recommended 0.5-2.5°C/Second Acceptable			To minimize solder balling, beading, hot slump
Soak Zone Profile	160-180°C/Recommended 150-200°C/Acceptable	30-90 Seconds Recommended 30-120 Seconds Acceptable	140-150°C/Recommended 130-170°C/Acceptable	May minimize BGA/CSP voiding
Time Above Liquidus (TAL)	235-250°C/Recommended 232-270°C/Acceptable	45-60 Seconds Recommended 30-100 Seconds Acceptable	198-213°C/Recommended 195-233°C/Acceptable	Needed for good wetting/reliable solder joint
Peak Temperature	260°C	—	230°C	As measured with thermocouple
Cooling Ramp Rate	2-6°C/Second Recommended 0.5-6°C/Second Acceptable			Rapid cooling promotes fine grain structure
Reflow Atmosphere	Air or N ₂			N ₂ typically preferred

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

www.indium.com

askus@indium.com

ASIA: Singapore, Cheongju, Malaysia: +65 6268 8678
 CHINA: Suzhou, Shenzhen: +86 (0)512 628 34900
 EUROPE: Milton Keynes, Torino: +44 (0) 1908 580400
 USA: Utica, Clinton, Chicago, Rome: +1 315 853 4900



©2016Indium Corporation

ISO 9001
REGISTERED