

PRODUCT DATA SHEET

Indium3.2HF Pb-Free

Water-Soluble Solder Paste

Introduction

Indium3.2HF is an air or nitrogen reflow, water-soluble solder paste specifically formulated to accommodate the higher processing temperatures required by the Sn/Ag/Cu, Sn/Ag, Sn/Sb, and other Pb-free alloy systems. This product formulation offers consistent, repeatable printing performance combined with a long stencil life and sufficient tack strength to handle the challenges of today's high-speed as well as high-mix surface mount lines. In addition to consistent printing and reflow requirements, this solder paste offers superb wetting to the various Pb-free metallizations and has exceptional low-voiding performance on fine-pitch components, including BGAs and CSPs.

Features

- Exceptional printing
- Long stencil life
- Good response-to-pause
- Wide reflow profile window
- Outstanding slump resistance
- Excellent wetting capability
- Superior fine-pitch soldering ability
- Low-voiding
- Halogen-free

Alloys

Indium Corporation manufactures low-oxide spherical powder composed of a variety of Pb-free alloys that cover a broad range of melting temperatures. Type 3 powder is the standard offering with Sn/Ag/Cu, Sn/Ag and Sn/Sb Pb-free alloy systems. The metal percent is the weight percent of the solder powder in the solder paste and is dependent upon the powder type and application.

Indium3.2HF Test Data Summary

Test	Result	Test	Result
J-STD-004* (IPC-TM-650)		J-STD-005* (IPC-TM-650)	
Flux Type (per J-STD-004A)	ORHO	Typical Solder Paste Viscosity SnAgCu, 89%, Type 3 Malcom (10rpm)	2,100 poise
Halide Content	0.0%	Typical Tackiness	50g
SIR	Pass	Slump Test	Pass
Wetting Test	Pass	Solder Ball Test	Pass
Electromigration	Pass		

All information is for reference only.

Not to be used as incoming product specifications.

*The most current revision of the applicable IPC Joint Industry Standard shall always be referenced.

Standard Product Specifications

Alloys	Powder Size	Printing	Dispensing
SAC305 SAC387	T3	88.50%	83.00%
	T4	88.25%	82.50%
	T4.5	88.25%	82.50%
	T5/T5MC	88.00%	82.00%

Packaging

Indium3.2HF is currently available in 500g jars or 600g cartridges. Packaging for enclosed print head systems is also readily available. Alternate packaging options may be available upon request.

Storage and Handling Procedures

Refrigerated storage will prolong the shelf life of solder paste. The shelf life of **Indium3.2HF** is no less than 6 months when stored at <10°C. Solder paste packaged in cartridges and syringes should be stored tip down.

When refrigerated, solder paste should be allowed to reach ambient working temperatures prior to use. Generally, paste should be removed from refrigeration at least 2 hours before use. Actual time to reach thermal equilibrium will vary with the container size and the solder paste temperature should be verified before use. Jars and cartridges should be labeled with the date and time of opening. It is not recommended to remove worked paste from the stencil and mix it with the unused paste in the jar, because this may alter the rheology of the unused paste.

Compatible Products

- **Rework Flux:** TACFlux®025-NP
- **Flux Pen:** FP-300
- **Cored Wire:** CW-301
- **Wave Flux:** 1095-NF

From One Engineer To Another®



PRODUCT DATA SHEET

Indium3.2HF Pb-Free

Water-Soluble Solder Paste

Printing

Stencil Design:

Electroformed and laser cut/electropolished stencils produce the best printing characteristics among stencil types. Stencil aperture design is a crucial step in optimizing the print process. The following are a few general recommendations:

- **Discrete components**—A 10–20% reduction of stencil aperture has significantly reduced or eliminated the occurrence of mid-chip solder beads. The “home plate” design is a common method for achieving this reduction.
- **Fine-pitch components**—A surface area reduction is recommended for apertures of 20mil pitch and finer. This reduction will help minimize solder balling and bridging that can lead to electrical shorts. The amount of reduction necessary is process dependent (5–15% is common).
- For optimum transfer efficiency and release of the solder paste from the stencil apertures, industry standard aperture and aspect ratios should be adhered to.

Printer Operation:

The following are general recommendations for stencil printer optimization. Adjustments may be necessary based on specific process requirement:

Recommended Printer Operation	
Solder Paste Bead Size	20–40mm in diameter
Print Speed	12–150mm/second
Squeegee Pressure	0.018–0.027Kg/mm of blade length
Underside Stencil Wipe	Start at once every 5 prints, then decrease frequency until an optimum value is determined
Solder Paste Stencil Life	>8 hours @ 60% RH and 22–28°C

Cleaning

Residue Removal

Indium3.2HF flux residues are water-soluble and best removed by an inline or batch type cleaning process using spray pressure and heated DI water. A spray pressure of 60psi and a DI water temperature of 55°C can be used as a starting point. The optimal spray pressure and temperature are a function of board size, complexity and the efficiency of the cleaning equipment and should be optimized accordingly.


Stencil Cleaning

This is best performed using an automated stencil cleaning system for both stencil and misprint cleaning to remove extraneous solder particles. Most commercially available stencil cleaners and isopropyl alcohol are acceptable.

Reflow

Recommended Profile:

Indium3.2HF should be reflowed using a linear profile in an air or nitrogen atmosphere. The stated profile recommendations can be used as a general guideline in establishing a reflow profile for **Indium3.2HF** with Sn/Ag/Cu, Sn/Ag, and Sn/Sb alloy systems.



Heating Stage:

A linear ramp rate of 0.5–2.0°C/second allows gradual evaporation of volatile flux constituents and helps minimize defects such as solder balling and/or beading and bridging resulting from hot slump. It also prevents unnecessary depletion of fluxing capacity when a high peak temperature and extended time above liquidus is used.

Liquidus Stage:

Indium3.2HF can accommodate a peak temperature range of 235–260°C. The actual peak temperature is determined by the board size, complexity, and component limitations. The time above liquidus (TAL) should be 30–90 seconds. A peak temperature and TAL above these recommendations can result in excessive intermetallic formation that can decrease solder joint reliability.

Cooling Stage:

A rapid cool down is desired to form a fine grain structure. Slow cooling will form a large grain structure, which typically exhibits poor fatigue resistance. The acceptable cooling range is 0.5–6.0°C/second (2.0–6.0°C/second is ideal).

Wetting

Indium3.2HF exhibits excellent wetting under both air and nitrogen reflow atmosphere. The solder joints are shiny and smooth, including those for ultrafine-pitch components. **Indium3.2HF** has low-voiding performance, including those for BGAs and CSPs.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

Contact our engineers today: askus@indium.com

Learn more: www.indium.com

ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900



©2018 Indium Corporation