

## PRODUCT DATA SHEET

# Activated Flux-Cored Wire

for Non-Sensitive Electronics and Electrical Applications

### Introduction

Indium Corporation has developed a range of flux-cored wire solutions to meet the needs of virtually every electrical and non-critical electronic assembly and rework operation. Flux-cored wire solutions are created when the desired alloy, cored wire flux, and flux percentage are combined into a void-free, perfectly layer-wound package, which can be easily used for both hand soldering and automated wire feed solder. Indium Corporation prides itself on providing the industry's widest range of flux-cored wire solders for both standard electronic assembly as well as highly specialized needs. No application is too large or too small.

### Activated Cored Wire Flux Formulations

- **CW-201 Standard Activated Rosin:** CW-201 is a traditional RA type flux as defined by the legacy Mil-Spec QQ-S-571. It uses traditional grade WW rosin and standard chloride activators. CW-201 is recommended for use with 63Sn/36Pb and 60Sn/40Pb alloys on non-sensitive oxidized copper parts, non-sensitive electrical/electronic assemblies where higher speed wetting is desired, assemblies where the residue is removed after soldering, and for soldering to moderately hard-to-solder metals such as brass and nickel.
- **CW-207 Activated Rosin for Lead-Free:** CW-207 is similar to CW-201 except that it is formulated using a blend of heat stable clear rosins. It is the standard option for soldering with lead-free alloy cored wire when soldering non-sensitive electrical or electronic applications, or when soldering moderately difficult-to-solder metals such as brass or nickel.
- **CW-209 Highly Activated Rosin:** CW-209 is exactly the same as CW-207 except with twice the amount of halogen activator. It is recommended for use where CW-207 or CW-201 are not active enough to solder to highly oxidized metals, or where speed of wetting is a high concern.

Formula	CW-201	CW-207	CW-209
Application	Fully Activated Rosin WRAP WW Rosin	Fully Activated Rosin	Highly Activated Rosin
IPC J-STD-004*	ROM1	ROM1	ROM1
IPC J-STD-004B*	ROM1	ROM1	ROM1
Rosin-Containing	Yes	Yes	Yes
Halogen-Free per JEITA ET-7304**	No	No	No
Actual Halogen Content***	<0.5%	<0.5%	<1.0%
Copper Mirror Corrosion IPC J-STD-004B	Pass	Pass	Pass
SIR J-STD-004B***	Pass	Pass	Pass
Electromigration J-STD-004B***	Pass	Pass	Pass
Color	Amber	Clear	Clear
Odor	Mild, rosin	Mild, sweet	Mild, sweet
Alloys	SnPb Alloys	Lead-Free Alloys	All Common and High-Lead Alloys

\* J-STD-004 and J-STD-004B vary in the way they measure halogen content. J-STD-004B finds both ionic and non-ionic halogen, whereas J-STD-004 will find ionic halogen, but most likely will not find non-ionic halogenated activators. Up to 500ppm combined halogen is considered halogen-free.

\*\* JEITA ET-7304 allows up to 900ppm chloride, 900ppm bromide, and up to 1,500ppm combined bromide and chloride to be considered halogen-free.

\*\*\* Data available upon request.

From One Engineer To Another®



Form No. 98848 R2

## PRODUCT DATA SHEET

# Activated Flux-Cored Wire

for Non-Sensitive Electronics and Electrical Applications

### Standard Flux Core Sizes, Alloys, and Shelf Life

Alloys	High Flux %	Medium Flux %	Low Flux %	Very Low Flux %	Shelf Life (<26°C & <60% RH)
SnPb <80% Pb	2.7–3.2%	1.7–2.2%	0.8–1.2%	–	3 years
Pb-Free Alloys	3.3–3.7%	2.7–3.2%	1.7–2.2%	0.8–1.2%	3 years
High Lead >80%	1.7–2.2%	1.3–1.7%	0.8–1.2%	–	1 year

Indium Corporation can produce many of the alloys on its alloys list as cored wire. Alloys containing greater than 20% bismuth, greater than 8% antimony, gold, or greater than 5% silver cannot be produced as cored wire at this time.

### Standard Diameters and Packaging

Inches	mm Equivalent	Tolerance	Packaging	Cartons
0.010"	0.25	±0.002"	1/4 lb	(10) 1/4 lb spools
0.015"	0.38	±0.002"	1/4 lb, 1 lb	(10) 1 lb spools
0.020"	0.50	±0.002"	1 lb	(10) 5 lb spools
0.025"	0.63	±0.002"	1 lb	per box
0.032"	~0.75	±0.002"	1 lb	—
0.040"	1.0	±0.002"	1 lb, 5 lb	—
0.062"	~1.5	±0.002"	1 lb, 5 lb, 20 lb	(2) 20 lb spools
0.120"	3.0	±0.002"	1 lb, 5 lb, 20 lb	per box

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

Contact our engineers today: [askus@indium.com](mailto:askus@indium.com)

Learn more: [www.indium.com](http://www.indium.com)



ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900



©2019 Indium Corporation