

PRODUCT DATA SHEET

Indium10.1

Pb-Free Solder Paste

Introduction

Indium10.1 is an air or nitrogen reflow, no-clean solder paste specifically formulated to accommodate the higher processing temperatures required by SnAgCu and other Pb-free alloy systems favored by the electronics industry to replace Pb-bearing solders. **Indium10.1** offers exceptional stencil print transfer efficiency to work in the broadest range of processes. In addition, the high oxidation resistance of **Indium10.1** virtually eliminates incomplete coalescence (graping) of small deposits and the head-in-pillow defect. **Indium10.1** also offers extremely low, large ground-plane voiding found in QFN components.

Features

- Low-voiding on QFN, BGA, and CSP components
- Exceptional head-in-pillow resistance
- High transfer efficiency and low variation through small apertures (≤ 0.66 AR)
- Eliminates the graping phenomenon
- Outstanding RF shield metallization wetting

Storage and Handling Procedures

Refrigerated storage will prolong the shelf life of solder paste. Solder paste packaged in cartridges should be stored tip down.

| Storage Conditions (unopened containers) | Shelf Life |
|--|-----------------|
| Cold storage ($< 10^{\circ}\text{C}$) | 12 months |
| Room temperature ($20\text{--}30^{\circ}\text{C}$) | 30 days maximum |

Solder paste should be allowed to reach ambient working temperature prior to use. Generally, paste should be removed from refrigeration at least 2 hours before use. Actual time to reach thermal equilibrium will vary with container size. Paste temperature should be verified before use. Jars and cartridges should be labeled with date and time of opening.

Packaging

Indium10.1 is currently available in 500g jars or 600g cartridges. Packaging for enclosed print head systems is also readily available. Alternate packaging options may be available upon request.

| Industry Standard Test Results and Classification | | | |
|--|------|---|-------|
| Flux Classification | ROL1 | Typical Solder Paste Viscosity for SAC305 T4.5 (Poise) | 1,450 |
| Based on the testing required by IPC J-Standard-004B | | Conforms with all requirements from IPC J-Standard-005A | |

*All information is for reference only.
Not to be used as incoming product specifications.*

Standard Product Specifications

| Alloy | | Metal Load | |
|---------|--------------------|------------|------------|
| Name | Composition | Type 3 | Type 4/4.5 |
| SAC387 | 95.5Sn/3.8Ag/0.7Cu | 88.75% | 88.5% |
| SAC305 | 96.5Sn/3.0Ag/0.5Cu | | |
| SAC105 | 98.5Sn/1.0Ag/0.5Cu | | |
| SAC0307 | 99Sn/0.3Ag/0.7Cu | | |
| SACm® | 98.5Sn/0.5Ag/1.0Cu | | |

Complementary Products

- **Rework Flux:** TACFlux® 089HF
- **Cored Wire:** CW-807
- **Wave Flux:** WF-9945, WF-9958

Other products may be applicable.

Please consult one of Indium Corporation's Technical Support Engineers.

From One Engineer To Another®



PRODUCT DATA SHEET

Indium10.1 Pb-Free Solder Paste

Printing

Stencil Design:

Electroformed and laser cut/electropolished stencils produce the best printing characteristics among stencil types. Stencil aperture design is a crucial step in optimizing the print process. The following are a few general recommendations:

- Discrete components—A 10–20% reduction of stencil aperture has significantly reduced or eliminated the occurrence of mid-chip solder beads. The “home plate” design is a common method for achieving this reduction.
- Fine-pitch components—A surface area reduction is recommended for apertures of 20mil pitch and finer. This reduction will help minimize solder balling and bridging that can lead to electrical shorts. The amount of reduction necessary is process dependent (5–15% is common).
- For optimum transfer efficiency and release of the solder paste from the stencil apertures, industry standard aperture and aspect ratios should be adhered to.

| Recommended Printer Operation | |
|-------------------------------|--|
| Solder Paste Bead Size | ~20–25mm in diameter |
| Print Speed | 50–100mm/second |
| Squeegee Pressure | 0.018–0.027kg/mm of blade length |
| Underside Stencil Wipe | Start at once per every 5 prints and decrease frequency until optimum value is reached |
| Squeegee Type/Angle | Metal with appropriate length/~60 degrees |
| Separation Speed | 5–20mm/second or per equipment manufacturer's specifications |
| Solder Paste Stencil Life | 18 hours (at 30–60% RH and 22–28°C) |


Cleaning

Indium10.1 is designed for no-clean applications; however, the flux can be removed, if necessary, by using a commercially available flux residue remover.

Stencil Cleaning is best performed using isopropyl alcohol (IPA) as a solvent. Most commercially available non-water-based stencil cleaners work well.

Reflow

Recommended Profile:



The stated profile recommendations apply to most Pb-free alloys in the SnAgCu (SAC) alloy system, including SAC305 (96.5Sn/3.0Ag/0.5Cu). This can be used as a general guideline in establishing a reflow profile when using **Indium10.1** Solder Paste. Deviations from these recommendations are acceptable, and may be necessary, based on specific process requirements, including board size, thickness, and density. Start with the linear profile, then move to the optional soak profile, if needed.

| Reflow Profile Details | SAC305 Parameters | | Comments |
|---|-----------------------|------------------|--|
| | Recommended | Acceptable | |
| Ramp Profile (Average Ambient to Peak)—Not the Same as Maximum Rising Slope | 1.0–1.5°C/second | 0.5–2.5°C/second | To minimize solder balling, beading, hot slump |
| Soak Zone Profile (optional) | 20–60 seconds | 30–120 seconds | May minimize BGA/CSP voiding Eliminating/reducing the soak zone <u>may</u> help to reduce HIP and graping |
| | 140–160°C | 140–170°C | |
| Time Above Liquidus (TAL) | 45–60 seconds | 30–100 seconds | Needed for good wetting/reliable solder joint |
| Peak Temperature | 230–260°C | 230–262°C | As measured with thermocouple |
| Cooling Ramp Rate | 2–6°C/second | 0.5–6°C/second | Rapid cooling promotes fine-grain structure |
| Reflow Atmosphere | Air or N ₂ | | N ₂ preferred for small components |

All parameters are for reference only.

Modifications may be required to fit process and design.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

All of Indium Corporation's solder paste and preform manufacturing facilities are IATF 16949:2016 certified. Indium Corporation is an ISO 9001:2015 registered company.

Contact our engineers: askus@indium.com

Learn more: www.indium.com

ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900



©2022 Indium Corporation