

APPLICATION NOTE

Indium Oxide and Indium-Tin Oxide (ITO) Coatings

General Properties

When applied as a coating to glass, mylar, or other transparent surfaces, indium oxide and indium-tin oxide (ITO) create conductive, highly transparent surfaces, which reflect infrared rays while allowing visible light and ultraviolet rays to pass.

Oxide-coated glass meets a wide range of demanding environmental requirements, due in part to the superior hardness and durability of the coatings.

While oxide coatings can be readily etched, they are resistant to most commercial solvents such as xylene, naphtha, acetone, methyl ethyl ketone, toluene, and mineral spirits. However, oxide coatings are soluble in dilute mineral acids.

Applications

Indium oxide and ITO coatings are used in a wide variety of applications such as solar collector panels, photovoltaic cells, low-E residential and commercial windows, liquid crystal display glass, aircraft windshields, highly efficient low-pressure sodium lamps, and transparent antistatic panels.

Limitations

Oxide-coatings are not recommended for prolonged exposure to temperatures greater than 150°C (300°F) in oxygen or air atmospheres, which may result in undesired changes in resistivity.

Coating Methods

Several methods for obtaining thin-films of ITO or In_2O_3 include gas phase hydrolysis, sputtering, and chemical vapor deposition.

ITO Technical Data

- **Electrical Resistivity:** Most ITO coated glass is available in surface resistivities from 5 ohms/square to 1,000 ohms/square.
- **Temperature Coefficient of Resistance:** For an average 50 ohms/square surface resistivity, the temperature coefficient of resistance is about $+2 \times 10^{-4}$ per °C(°F).
- **Service Temperatures:** Generally, ITO coatings are stable up to 150°C (300°F). Surface resistivity increases about 10% following exposure to 205°F (400°F) for one hour. The rate increase accelerates at higher temperatures.
- **Refractive Index:**
 - Substrate glass – 1.52
 - ITO-coated glass – 2.0
- **Transmittance and Reflectance:** Visible transmittance of ITO-coated glass is from 75–90% for glass substrate thicknesses ranging from 0.5–6.0mm. Typical reflectance measurements range from 8–25%.
- **Materials Available:** While Indium Corporation is not engaged in the actual application of coatings to substrates, a wide variety of indium-bearing materials are available for rapid delivery. These materials include indium oxide; indium-tin oxide; pure indium metal; and indium, tin, and alloys for chemical vapor deposition.

This application note is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

All of Indium Corporation's solder paste and preform manufacturing facilities are IATF 16949:2016 certified. Indium Corporation is an ISO 9001:2015 registered company.

From One Engineer To Another®

Contact our engineers: askus@indium.com

Learn more: www.indium.com

Form No. 97524 R5

ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900



©2022 Indium Corporation