

PRODUCT DATA SHEET

1075-EXR-40

VOC-Free No-Clean Wave Solder Flux

Introduction

1075-EXR-40 is a non-halide, synthetic resin flux specifically developed for wave soldering surface mount, mixed technology and through-hole electronic assemblies.

1075-EXR-40 is a water-based, non-flammable formulation eliminating special storage requirements, and dramatically reducing VOC emissions. **1075-EXR-40** is formulated to reduce solder balling and provide excellent solderability on difficult-to-solder assemblies.

Features

- VOC-free formulation
- Excellent surface wetting
- Eliminates cleaning
- Increased activity
- Reduces solder balling
- Conforms to Telcordia GR-78 specification

Process Recommendations

1075-EXR-40 can be applied by spray or wave. Topside board temperatures for most circuit board assemblies can range from 93–115°C depending on equipment, board size, board complexity, and conveyor speed (typically 4–6'/minute). Preheat should be adjusted to ensure complete water removal before contact with the solder wave. Convection preheat is strongly recommended for optimum results.

Because **1075-EXR-40** is water based, it does not require frequent acid value monitoring. If thinning is required, the addition of deionized water is all that is necessary.

1075-EXR-40 may freeze if exposed to temperatures below 0°C. The material is not affected by freezing. If the flux becomes frozen, bring to room temperature until thawed, then agitate.

Physical Properties

Test	Result
Color	Clear
Specific Gravity @ 25°C (77°F) @ 15.5°C (60°F)	1.019 1.019
Acid Value	40.0
Solids Content	5.0
Flash Point	None
Silver Chromate Paper Text	Pass
Copper Mirror Test*	Pass
Freeze/Thaw Test	Pass
J-STD-004 Flux Type	ORLO

***Modified IPC/Bellcore Method:**

Passes the Copper Mirror Test when the same flux is formulated with isopropanol or the solids from the water-based formulation are reconstituted with isopropanol.

Packaging

- 5-gallon containers
- 55-gallon drums

Safety

1075-EXR-40 is a non-flammable material. Standard precautions should be observed when handling this material.

Technical Support

Indium Corporation's internationally experienced engineers provide in-depth technical assistance to our customers. Thoroughly knowledgeable in all facets of Material Science as it applies to the electronics and semiconductor sectors, Technical Support Engineers provide expert advice in solder properties, alloy compatibility and selection of solder preforms, wire, ribbon, and paste. Indium Corporation's Technical Support Engineers provide rapid response to all technical inquiries.

Safety Data Sheets

The SDS for this product can be found online at <http://www.indium.com/sds>

From One Engineer To Another®



PRODUCT DATA SHEET

1075-EXR-40

VOC-Free No-Clean Wave Solder Flux

Telcordia Surface Insulation Resistance Test

Test Pattern	Boards	Initial Reading*	Final Reading*
IPC-B-25A	Control	8.33×10^{11}	6.76×10^{11}
0.0125" Wide Lines	Pattern up	4.79×10^{10}	7.41×10^{11}
0.0125" Spacing	Pattern down	1.43×10^{11}	2.17×10^{11}

*All readings expressed in Ohms.

Telcordia Electromigration Resistance Test

Test Pattern	Boards	Initial Reading*	Final Reading*
IPC-B-25A	Control	5.32×10^{10}	2.23×10^{11}
0.0125" Wide Lines	Pattern up	2.18×10^9	1.14×10^{11}
0.0125" Spacing	Pattern down	1.57×10^{10}	1.50×10^{10}

*All readings expressed in Ohms.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

Contact our engineers: askus@indium.com

Learn more: www.indium.com



ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900



©2019 Indium Corporation