

## PRODUCT DATA SHEET

# Commercial Indium Metal

### Introduction

Indium Corporation is the leading global supplier of **commercial indium**, high-purity indium, indium fabrications, alloys, and compounds. Indium metal is extracted from indium-bearing ore and is refined to various grades in high-volume utilizing state-of-the-art SPC-controlled refining technologies. Rigorous quality standards and advanced analytical instrumentation, such as ICP and GDMS, ensure consistent product quality lot to lot.



### General Properties and Applications of Commercial Grade Indium

Indium is a versatile metal with unique physical properties. Following are some of the unique properties of indium and a sampling of innovative applications for the metal:

- Indium has a low melting point of 157°C but a high boiling point of 2,080°C, one of the highest liquidus temperature ranges of any metal.
- Indium has a low vapor pressure making it ideal for use in high vacuum applications.
- Indium is soft, pliable, and malleable, even down to cryogenic temperatures approaching absolute zero. It will form a hermetic gasket seal between two mating metal parts. Being soft, indium deforms and fills in the microstructure of two mating parts, pressed together using moderate pressure. Similarly, indium can be used as an efficient thermal conductive interface in electronics.
- Indium has relatively low toxicity.
- Indium is a bright shiny metal that forms a thin (80–100 angstroms) protective oxide layer. It is used as a decorative trim coating metallization on plastics used in appliance and automobile trim.
- Indium will cold-weld to itself, making it useful for bonding parts or assemblies together.
- Indium effectively reduces the melting point in solder alloys and fusible alloys.
- Indium in small percentages improves the thermal fatigue performance of solders used in electronics assembly.
- Indium will bond to glass, quartz, and certain ceramics and oxides.
- Indium will compensate for differing thermal coefficients of expansion of mating parts.
- Used in small amounts, indium hardens certain metals and alloys; it hardens gold used in electronics and dental alloys.
- Indium coatings provide lubricity in sleeve bearings such as those used in aircraft piston engines and industrial machinery.
- Indium is a neutron absorber and is used in radiation detection badges.

### Available Physical Forms of Indium

- Ingot
- Wire
- Tubing
- Foil
- Ribbon
- Plating anodes
- Sacrificial anodes
- Sheet
- Shot
- Powder
- Custom preforms

### Grades Available

- 3N (99.9%)
- 4N (99.99%)
- 4N5 (99.995%)
- 5N (99.999%)

For higher grades, please refer to the High-Purity Indium Metal product data sheet.

**From One Engineer To Another®**



## PRODUCT DATA SHEET

# Commercial Indium Metal

### Typical Impurities

More than 95% of our past production lots show the following elements as impurities below the provided ppm levels. The ppm levels do not represent the maximum, or minimum for a specific lot and should not be used in designing product specifications. Impurities will vary across different lots of indium, but the total impurities in each lot will always be below the maximum allowed for each purity grade:

- 3N grade: total impurities <1,000ppm
- 4N grade: total impurities <100ppm
- 4N5 grade: total impurities <50ppm
- 5N grade: total impurities <10ppm

Element	3N Grade (ppm)	4N Grade (ppm)	4N5 Grade (ppm)	5N Grade (ppm)
Ag	30	30	22	2
Bi	24	8	3	2
Cd	7	4	3	2
Cu	8	5	4	2
Fe	22	4	3	2
Ni	66	4	3	2
Pb	41	41	4	2
Sn	107	78	23	2
Ti	5	4	3	2

### Oxidation and Shelf Life

Compared to most metals, indium oxidizes quite slowly. Immediately after fabrication, there is initial rapid oxide growth for a few days until the oxide thickness reaches 80–100 angstroms. If stored in air, the oxide thickness slowly increases over several months depending on storage conditions and the physical form of indium. For physical forms of indium that have a high surface area such as powder, storage in an inert gas such as argon with a desiccant will greatly reduce oxidation formation.

Following are the shelf lives depending on the physical form of indium:

- Indium ingot—12 months
- Indium shot—6 months
- Indium powder—3 months

In some cases, excessive oxidation can be removed by immersion in dilute mineral acids. Please contact technical support for more information.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

*All of Indium Corporation's solder paste and preform manufacturing facilities are IATF 16949:2016 certified. Indium Corporation is an ISO 9001:2015 registered company.*

Contact our engineers: [askus@indium.com](mailto:askus@indium.com)

Learn more: [www.indium.com](http://www.indium.com)

ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900

### Technical and Customer Support

Indium Corporation's internationally experienced engineers, material scientists, and metallurgists provide in-depth technical assistance to our customers. Thoroughly knowledgeable on all aspects of material science and metallurgy as it pertains to indium metal, its uses, and applications, our technical service staff is available to provide rapid response to all technical inquiries. We believe that our long-standing emphasis on providing our customers with superior technical service clearly differentiates Indium Corporation from our competitors.

### Safety Data Sheets

Please refer to the SDS document within the product shipment, or contact our local team to receive a copy.



©2024 Indium Corporation